

FOIL AND FILM BARRIERS

Typical barrier values

Polymer/Barrier	Grammage (g/m ²)	Water Vapour Permeability (g/m ² /24 h)		Oxygen Permeability (cm ³ /m ² /24 h/atm)	
		23°C, 50% RH	38°C, 90% RH	23°C, 50% RH	38°C, 90% RH
Metalprint	25	16	65	110	150
AlubARRIER	57	<0.01	<0.01	<0.01	<0.01